

LDPE

Model	Density [g/cm³]	MFI [g/10min] (2,16 kg, 190 °C)	Processing	Applications
2100TN00	0,921	0,3	Blown film extrusion	Shrink hoods, industrial sacks, carrier bags and liners
Tasnee LD 0725N	0,923	0,75	Blown film extrusion	Bags & pouches, medium duty bags, shrink wrap film, agricultural Film, food packaging film
Tasnee LD 1925AS	0,925	1,9	Blown film extrusion	Bags & pouches, shrink film, food packaging, surface protection

HDPE

Model	Density [g/cm³]	MFI [g/10min] (2,16 kg, 190 °C)	Processing	Applications
Marlex HHM TR-144	0,946	0,18	Blown film extrusion	T-shirt bags, multi-wall liners, trash bags
Marlex HHM TR-131	0,938	0,20	Blown film extrusion	T-shirt bags, shopping bags, trash bags
Marlex HHM 5502BN	0,955	0,35	Blow moulding	Bottles, ice chests and coolers, household and industrial containers, food packaging, pharmaceuticals
Uz-Kor BL5200	0,963	0,32	Blow moulding	Bottles, toys
Uz-Kor BL6200	0,958	0,35	Blow moulding	Bottles, household containers
Uz-Kor FL7000	0,956	0,035	Blown film extrusion	Shopping bags, garbage bags, general and industrial packaging
LG Chem Lucene SM800	0,955	8	Injection moulding	Caps & closures for beverage bottles, cartridge, pail

PP

Model	Density [g/cm³]	MFI [g/10min] (2,16 kg, 230 °C)	Processing	Applications
<i>HOMO</i>				
Natpet Teldene H03BPM	0,9	3	Extrusion, co-extrusion, thermoforming	BOPP, metallizable film, raffia, automative compounding
Natpet Teldene H03ML	0,9	3,2	Extrusion, co-extrusion, injection moulding	Housewares, toys, small appliance parts, raffia, automotive compounding
Natpet Teldene H25FBA	0,9	25	Fiber extrusion, bulk filament extrusion, Co-extrusion	Continous filament, staple fiber, upholstery, automotive compounding
LG Chem Seetec MH1850	0,9	60	Injection moulding	Disposable food containers, housewares, thin- walled containers
<i>COPO</i>				
LG Chem Seetec M1850	0,9	70	Injection moulding	Yoghurt containers, thin-walled containers